

TECHNICAL DATA SHEET

KEXCELLED PLA K5Silk

Product code:	Revision Number:	Revision date:	TDS No.:
PLA K5Silk	02	09/03/2020	KT04.012.0152

BRIEF INTRODUCTION

Filament suitable for all commercially available leading brands FDM/FFF Printers.

CHARACTERISTIC

high gloss finish and silk-like surface | higher impact strength than normal PLA | non-irritating odor.

IDENTIFICATION OF THE MATERIAL

Trade name	PLA K5Silk
Chemical name	Polylactic Acid
Use	3D printing
Origin	KEXCELLED

GUIDELINE FOR PRINT SETTINGS

Nozzle temperature	220±10°C
Bed temperature	0~60°C
Bed modification	Tape or glue below 60°C
Active cooling fan	ON, 100%
Shell thickness	≥0.8mm
Print speed	40-80mm/s

Settings are based on a 0.4mm nozzle.

MATERIAL PROPERTIES

		Test Method
Melt temperature	~160°C	ISO 11357
Glass transition temperature	~60°C	ISO 11357
Melt flow rate (MFR)¹	8±2 g/10min	ISO 1133
Heat deflection temperature(HDT)²	52°C	ISO 75
Vicat softening temperature(VST)³	/	ISO 306
density	1.24g/cm ³	ISO 1183
Odor	Odorless	/
Solubility	Insoluble in water	/

1.test conditions: T= 190°C; m=2.16 kg.

2. test conditions:0.45MPa;120°C/h.

3. test conditions:10N; 120°C/h.

MECHANICAL PROPERTIES|TENSILE TEST **Test Method ISO 527**

All test specimens were printed using an FlashForge Guider 2s under the following conditions:

- Printing temperature: 220°C
- Heated bed temperature: 50°C
- Print speed: 50mm/s
- Shell thickness: 0.8mm
- Infill under 45°



Infill	Printed horizontal X,Y-axis 100%
Tensile strength (Mpa)	41.5
Force at break (Mpa)	/
Elongation at break (%)	10
Tensile modulus (Mpa)	2100

MECHANICAL PROPERTIES|IMPACT TEST **Test Method ISO 179**

The same conditions as tensile test.

1→impact direction



Infill	Charpy(ep) 100%
Impact strength (KJ/m ²)	22.5
Notch impact strength ¹ (KJ/m ²)	6

MECHANICAL PROPERTIES |FLEXURAL TEST **Test Method ISO 178**

The same conditions as tensile test.

1→bending direction



Infill	Normal 100%
Maximum force (Mpa)	70.5
Flexural modulus (Mpa)	2650
1.notch type: type A	

FILAMENT SPECIFICATION		Test Method
Diameter 1.75mm	1.75±0.03mm	EX1125
Diameter 2.85mm	2.85±0.03mm	EX1125
Diameter 3.00mm	3.00±0.03mm	EX1125
Max roundness deviation (1.75)	0.03mm	EX1125
Max roundness deviation (2.85)	0.03mm	EX1125
Max roundness deviation (3.00)	0.03mm	EX1125
Net weight on reel	1kg	EX1125