



# Test Report

Report No.: DGC170217003F02

Page 1 of 3

**Applicant** : Cotronic Technology Limited  
**Address** : Rm. 1407, 14/F, Worldwide Industry Center, 43-47 Shan Mei Street, Fotan Shatin, Hong Kong.

**The following sample(s) was/were submitted and identified on behalf of the client as:**

**Product Name** : Nose Aspirator  
**Model** : ASPI  
**Manufacturer** : Cotronic Technology Ltd  
**Address** : Floor 4~6, Block 7, West of ZhouShi Road, XiXiang Street, BaoAn Zone, ShenZhen, GuangDong, China

**Date of Sample Received** : Feb. 17, 2017  
**Test period** : Feb. 17, 2017 - Feb. 23, 2017

**Test requested:**

For material which contact with foodstuff, selected tests were performed for compliant with the following regulations:

- Regulation 1935/2004/EC on materials and articles intended to come into contact with food;
- Regulation (EU) No.10/2011: On plastic materials and articles intended to come into contact with food and amendment regulation (EU) 2016/1416.

**Test method** : Please refer to next page.

**Test result** : Please refer to next page.

**Tested by:** Min

**Reviewed by:** Sary

**Approved by:** Sary

**Date:** Feb. 23, 2017



This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**NTEK Testing Technology Co., Ltd.**

**Address:** No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China  
**Tel:** (+86-769) 23301666 **Fax:** (+86-769) 23301600 **Email:** service@ntek.org.cn **http://www.dgntek.org.cn**



# Test Report

Report No.: DGC170217003F02

Page 2 of 3

## Test Results:

Specific migration of Phthalates test:

Method: 3% Acetic Acid, 40°C, 0.5h, determined by GC-MS.

Test Item	Unit	Limit	MDL	Result	
				No.1	No.2
Dibutylphthalate (DBP)	mg/kg	0.3	0.1	N.D.	N.D.
Butylbenzylphthalate (BBP)	mg/kg	30	0.1	N.D.	N.D.
Di-(2-ethylhexyl)-phthalate (DEHP)	mg/kg	1.5	0.1	N.D.	N.D.
Di-n-octylphthalate (DNOP)	mg/kg	60	0.1	N.D.	N.D.
Di-iso-nonylphthalate (DINP)	mg/kg	60	0.5	N.D.	N.D.
Di-iso-decylphthalate (DIDP)	mg/kg	60	0.5	N.D.	N.D.
Conclusion				Pass	Pass

## Test Part Description:

No.1: Transparent PC

No.2: Translucent silicone

## Note:

- (1) mg/kg=ppm=0.0001%;
- (2) N.D.=Not Detected(<MDL);
- (3) MDL=Method Detection Limit.

This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**NTEK Testing Technology Co., Ltd.**

Address: No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China

Tel: (+86-769) 23301666

Fax: (+86-769) 23301600

Email: [service@ntek.org.cn](mailto:service@ntek.org.cn)


<http://www.dgntek.org.cn>

# Test Report

Report No.: DGC170217003F02

Page 3 of 3

## Photographs of Samples:



\*\*\*End of Report\*\*\*

This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**NTEK Testing Technology Co., Ltd.**

Address: No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China

Tel: (+86-769) 23301666

Fax: (+86-769) 23301600

Email: [service@ntek.org.cn](mailto:service@ntek.org.cn)

<http://www.dgntek.org.cn>